Notebook Series -- Notebooks by Edison
Notebook, N-19-01-01.1

This notebook is a continuation of N-18-12-26.2. It was used by Edison during the period January-February 1919 to continue his experiments on processing lithium ores, including lepidolite (lithium mica), amblygonite, and spodumene. The experiments probably relate to Edison's use of lithium oxide in the electrolyte for storage batteries. The entries describe the reagents used to treat the amblygonite or lepidolite and note the presence of a lithium "line" as indicated by a spectroscope. One entry provides an extended description of a "factory process" for spodumene and lepidolite "in case any accident occurs" to Edison, who was about to leave West Orange for his winter home in Fort Myers, Florida. His description includes instructions for processing a ton of ore, as well as a suggestion that the ores should be purchased along with a mine "for reserve." The front cover is labeled "Lithia 2." The pages are unnumbered. Approximately 30 pages have been used.

63 -

10 Amblg floated
5 Magnesium Sulphate
at 1st - only -
On 1130 am - 3rd

Hardly any Lens
9 more put 10 grms
Lens on
4th 11 am poor Lens
25 Sec with H@P -
Abandoned

CIJ

I will make a Deep with
15 grams — as only 3 grms
here which is extremely
unsatisfactory.

64-

1.0 amblig floated
3 Magnesium Hydrox
only at 1st — 3 pm 3rd

No line —

Put on hot plate all night
July 4th 1030 am.
Can see line for 100 sec
This shows Mg hydrox (no HCl)
as a base like Lime but on
account of poor solubility
acts much more slowly
50 sec with HCl & follows —
put back on plate 1030 am 4th
after filtering off & saving 1st
filtrate —
with ~~Chloride~~ (HCl) get slow line
Disappears 30 seconds — This
appears to be working

65

10 ambleq - floated
3 Mg hydrox
2 Sulphate dessss

only got dull line -
Count 33. acc
put some Hel in it
250cc —
Y ~~xxxx~~ I leave on all
night. by mistake not
put on hot plate now on
Jany 4 12 noon
Y to gives dull line - Not good
Y guess Abandoned

[C5]

This is best yet with
10 000 CC get a
Considerable better line
than 40 Mdq/250 cc
standard -
The residue is considerable
What is the reaction.

Total residue in 10000
CC after Evap



Very small -

66 -

10 grms Ambly floated
10 grms Sodia chemi -
Very strong line
but not so strong
as 69 - as no chloride
Counted 200 seconds
& still running -
on all night
Jan 4 12 noon, strong
line, now following



67

10 cubic floated
4 grms Sodium Hypposulfite
250cc after 4 hours
not strong line but
Count 18 before
disappeared —
9 hours all night
on plate, 5 pm 3rd
Jan 4 Cant even get a
line - Count worse
Abandoned

68 =

10 ambien floated

1 gram KOH -

10 Lime —

Without HCl get rather dull line 200 seconds but with HCl - bright line only 30 seconds

Burning rather poorly

250 cc on all night

Jan 4 12 noon 150 dim

without HCl 30 seconds with a bright

NG - Abandoned

6000 cc equals 40
this is not as good as
HCl or H_2SO_4 - Later
used 9000 cc
But $FeCl_2$ was more +
part ferric & decomposed
2nd wash filters no
clear but more 50 cc
not passed when wash
& put under in filtrate
but line is dull —

69 — FeCl seems old & decomposed when dissolved by reagent —

10 Ammonium Chloride
10 Ferrocyanide

Very brilliant - Counted
200 seconds & line still
strong. 250 cc —
line still good at 200
on all right.

Make some good Chloride
+ try def ammonium —
Jan 4 11 am - line just as strong
filtrate Neutral ! !
Saved filtrate & put residue
back on hot plate —
2nd filtrate slimy almost
impossible to filter 250 cc
40 line or better

showing that of Lime was given on account of slight Solubility of the Oxide. The whole Lime probably has got out

There is better than Lime, Barium or Strontium or any of the other Combination of Alkaline reaction & 10cc work

of Course the way I use it much of the Oxide must be Carbonated,

70.

10 Amblygonite floated

11 gram Magnesium Oxide –

Water blues Rd/Litmus night away – on 6pm 5th

930 am Jany 6 – gives good line put back on plate 940 am 6th –

with the 750 cc 1st & 2nd

filtrate with HCl get

38 seconds line –

if the filtrate, four line well and HCl – now in Febry & 10 am for 5th Leach –

Sunday 9th Febry put all together & got 4000 cc but last 18 hours soak filtrate was very strong lime

(15)

71-

10 amblygonite floated
20 grammes Magnesium Carbonate

Thus also blues red litmus paper
but not to quench no Oxide —

Mg

Idea is to get HCl.

72

10 cc Blyonetta flooded

10 grains Magnesium Sulphate

10 " " NaCl—

Thereafter ½ hour is most slightest acid. + remarks 73

15 hours more neutral

6000 CC—

to make 100 c.c.

73.

10 Ammon. ffloccled
10 Ferrous Sulphate
10 NaCl.

This quickly becomes very slightly acid.
After 15 hours slightly acid
after 30 hours very strong
lime 250 cc — Odd absence of
fellers qcad —

Only gives 6500 cc Equal
to 40 mlg standard —

C21

I added 1/2 & Evaporated it down — Residue not over

~~Pb~~ 1 grain — S S
! !

Wonderful

Soda alum or Mg ~~sulphate~~ H_2SO_4 good for ammoniacals

10 Ammoniacals
5 Soda Alum —
shows acid on Alum

after 15 hours I find it is not acid —

gives fairly strong line at End of 400 seconds
no acid 200 cc

Took 1/2 of filtrate 1+2nd and it required 5000 cc to Equal 40 or total 10000 cc
This is as good as 10 alum & shows 5 alum is Enough

75

10 grms Arabic floated

10 grms Sulphate Alumina

This brake

as I put it under back
+ forgot it -
I filtered it, of course to
only water level
250 cc beaker then 40
probably 400 cc
more volume would
be 8400 cc

10 milligrams floated
7 = grams Sulphate of
Alumina —

In 20 minutes after
boiling on hot plate.
I filtered a little at it
more 20 seconds.
with 250 cc in beaker
then on going done
1st filtrate filters quad—
on ~~30~~ 20 hours -

8000 cc Equals
40 mlg - dont think
got all out — time too short

Must now decide between Alum + Sulphate Aluminum alone — Costs + time — to determine as well as residue unfiltrate —

or H_2SO_4 or MgO or Dolomite

77

10 cu/cm floated

2½ grains.

Aluminum Sulphate

after ½ hour on hot plate 250 cc to acid to Litmus

Feby 7 4pm —

Feby 8 10 am slightly acid good line —

filtering — filters rather slow but clear —

2nd batch for 3 hours, got a little filters very slow —

About 6500 to 7000 cc

Equals 40 Mlq Standard

78

10-Lepidolite -
10 Soda Alum

for a quick test,

In case any accident occurs to me following process will work on a factory process for Spodumene & Lepidolite -

Break up in Crusher to 1" or less the ore, bring to yellow & then suddenly quench in water - Draw off water - Dry ore & Crush in ball mill etc to very fine powder - Pass this through packed Classifier & only take the ore of float that shows under Microscope to be 100 of mesh diameter - The other ore to be dried & regrinded - Grind dry as wear & power costs more than drying if wet crushing is done -

for 1 ton of ore - use about
1 Ton Caustic best grade Lime
10 Ton Ore, Use several iron tanks. Each holding Ton of ore with stirrer which can go very slow as 5 Rev min to keep from Coloring on bottom heavily lag under top, & bottom with Regulation lagging but Extra heavy just enough deep & heavily paint to keep inside of lagging.

Have a set of tanks, after say 3 days withdraw the mix to a filter press, & pass the filtrate to 2nd tank & break up filter Cakes & put back in 1st tank - after ~~3 days~~ put fresh water in 1st tank & after say 3 days filter press 2nd tank - the filtrate from 2nd tank put back in 2nd tank after press 1 Tank & put filtrate in 2nd Tank & thus 3 washings of 1 tank will Exhaust it & so on the original solution should weigh 10 tons & strength & strength until finally it very strong, It then can be Evaporated down by a 2 or 3 stage Yaran Vacuum Evaporator till ready to Extract the Lithium -

With Auxiliary Wooden Tanks are necessary & 2 pumps on

& carry on to full extraction
Magnesium Oxide &
get precedence,

Remarks before
leaving for Fla —

Try Clay & H_2SO_4 -
heated but not so it
dont go to a soup
etc & test —
also H_2SO_4 alone &
afterwards Lime
also alum (Na) &
also Sulfate Aluminum
also Bisulfate soda

Thereon lepidolite & also
Spod - but think
Lime for Spod so OK
& perhaps Lepidolite

(15)



Continued

1 Ton or 7/10 Ton of alum (soda) — or 7/10 of 6 Sulphate of aluminum or 1 Ton of 60 Baume acid Can be used,

As Ambling needs an acid salt — Thus used many times a week for than Spread of Lep with the alkali as Lime dissolves very slightly & requires time while Alum or Aluminum Sulfate or H_2SO_4 dissolves Easily —

I am not sure but think the Lime Extraction has alkali in form of Hydroxides —

Ambling I think is a Sulphate. —

~~For~~ for battery The K or Na need not be separated out

all made hydroxide + allowed for,

If there is trouble with final solution may have to evap down for crystals of Li Cl Na Carbonate + then Causticize with Lime as above described —

If the residue is full of Alum or Na_2SO_4 probably Carbonate method or alcohol ~~etc~~ or Crystallization take most out Orange Dye & take best pieces for facets + buy ore + also purchase ores or mixture of best mixes for reasons of $20.00 each to reasons

but dont attempt to mine best leases + buy on a % of Li
3% Spod $5 - 3½ $6 4% $7
Lepidolite 6 7 8
Amblig - $15. for 8% + less
as % goes down Li_2O is basis —

Amblygonite Dols may have to be Limed (10) Caustic but well take out alumina of fluorine + Phosphorus